

SikaHyflex®-250 Facade

High-performance over paintable 1-part professional weatherproofing sealant for concrete, masonry and EIFS facades

Construction

Product Description SikaHyflex®-250 Facade is a 1-part, moisture curing, and low modulus elastic joint sealant suitable for movement and connection joints in commercial building envelopes.

Characteristics / Advantages

- Very good weathering and ageing resistance
- Movement capability of + 100/50 % (ASTM C719)
- Bubble-free curing
- Low stress to the substrate
- Easy to smooth and very good workability
- Very good adhesion to many substrates
- Solvent free and odourless
- Very low emission

Approvals / Standards

Conforms to EN15651-1 F EXT-INT CC 25 LM
Conforms to ISO 11600 F 25 LM
Conforms to DIN 18540 F
Conforms to ASTM C920, class 100/50
EMICODE EC 1^{PLUS}R, very low emission
ISO 16938-1 non staining on marble
ASTM C 1248 non staining on marble

Specific Ratings	LEED® EQc 4.1	SCAQMD, Rule 1168	BAAQMD, Reg. 8, Rule 51
	passes	passes	passes

Product Data

Colours White, black, concrete grey.
Further colours available upon request

Packaging 600 ml foil pack, 20 foil packs per box, 960 foil packs per pallet

Storage Conditions / Shelf-Life 15 months from date of production if stored in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +5°C and +25°C.



Technical Data

Chemical Base	i-Cure® technology polyurethane	
Density	1.35 kg/l approx	(CQP ¹⁾ 006-4, ISO 1183-1)
Sag Flow	0 mm (20 mm profile, 50°C)	(CQP 061-4, ISO 7390)
Skin Time	70 minutes approx. ²⁾	(CQP 019-1)
Tooling Time	50 minutes approx. ²⁾	(CQP 019-2)
Curing Rate	3 mm/24 h approx. ²⁾	(CQP 049-2)
Movement Capability	±25%	(ISO 9047)
	+100%/-50%	(ASTM C719)
Shore A Hardness	20 after 28 days approx. ²⁾	(CQP 023-1, ISO 868)
Tear propagation resistance	5 N/mm approx. ²⁾	(CQP 045-1, ISO 34)
Secant Tensile Modulus	0.3 N/mm ² approx. at 100% elongation ^{2), 3)}	(CQP 020-1, ISO 8339)
	0.6 N/mm ² approx. at 100% elongation (-20°C) ³⁾	
Elongation at Break	800% approx. ²⁾	(CQP 036-1, ISO 37)
Elastic Recovery	> 75% ^{2), 3)}	(ISO 7389)
Application Temperature	+5°C to +40 °C, min. 3°C above dew point temperature	
Service Temperature	-40°C to +70°C	

¹⁾ Sika Corporate Quality Procedure

²⁾ 23°C / 50% r.h.

³⁾ conditioning: Method B

Application Details

Joint Design/ Consumption

The joint width must be designed to suit the movement capability of the sealant. In general the joint width should be > 10 mm and < 40 mm. A width to depth ratio of approx. 2:1 must be maintained.

Standard design dimensions for concrete elements as per DIN 18 540 /table 3:

Joint distance [m]	2	4	6	8	10
Min. joint width [mm]	10	15	20	28	35
Min. joint depth [mm]	10	10	10	14	17

*ΔT is considered to be the difference between the highest expected temperature in use (or lowest, check which case leads to higher ΔT) and the application temperature.

All joints must be properly designed and dimensioned in accordance with the relevant standards, before construction. Basis for calculation of the necessary joint width are the technical values of the joint sealant and the adjacent building materials, as well as the exposure of the building, type of construction and its dimensions.

Approximate consumption

Joint width [mm]	10	15	20	25	30
Joint depth [mm]	10	10	10	12	15
Joint length / 600 ml [m]	6	4	3	2	1.3

Backing: Use closed cell, polyethylene foam backing rods.

Substrate Preparation / Priming	<p>SikaHyflex®-250 Facade generally has strong adhesion without primers/activators to most clean, sound substrates.</p> <p>For optimum adhesion and critical, high performance applications such as multi story building work, high stress bonding joints, extreme weather exposure or water immersion the following procedure shall be followed:</p> <p><u>Non porous substrates</u></p> <p>Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated with Sika® Aktivator-205 by using a clean towel. Before sealing allow a flash-off time >15 min (max.6 hours).</p> <p>Metals like copper, brass, titanium-zinc etc. have to be cleaned and pre-treated with Sika® Aktivator-205 by using a clean towel. After a flash-off time >15 minutes, apply Sika® Primer-3 N by using a brush and allow a flash-off time >30 minutes (max. 8 hours) before sealing.</p> <p>PVC has to be cleaned and thereafter pre-treated with Sika® Primer-215 by using a brush. Before sealing allow a flash-off time > 30 min (max.8 hours).</p> <p><u>Porous substrates</u></p> <p>Concrete, aerated concrete and cementitious plasters, mortars, brick, etc. have to be primed with Sika® Primer-3 N by using a brush. Before sealing allow a flash-off time >30 minutes (max. 8 hours).</p> <p>For detailed instructions consult the Product Data Sheet for pre-treatments or contact our Technical Service Department.</p> <p>Primers are adhesion promoters. They neither substitute for the correct cleaning of the surface nor improve their strength significantly.</p>
Application Method / Tools	<p>SikaHyflex®-250 Facade is supplied ready to use.</p> <p>After suitable substrate preparation, insert backing rod to the required depth and apply primer if necessary. Insert foil pack into sealant gun and extrude SikaHyflex®-250 Facade into joint making sure that it is in full contact with the sides of the joint and avoid air entrapment. SikaHyflex®-250 Facade must be tooled firmly against joint sides to ensure good adhesion.</p> <p>Masking tape may be used where exact joint lines or exceptionally neat lines are required. Remove the tape within the skin time. Use a compatible tooling agent (e.g. Sika® Tooling Agent N) to smooth the joint surfaces. Do not use solvent containing products!</p>
Cleaning of Tools	<p>Clean all tools and application equipment with Sika® Remover-208 / Sika® TopClean-T immediately after use. Once cured the material can only be removed mechanically.</p>
Further Documents available	<ul style="list-style-type: none"> ■ Safety Data Sheet (SDS) ■ Pre- treatment Chart Sealing & Bonding ■ Method Statement Joint Sealing ■ Method Statement Joint Maintenance, Cleaning and Renovation ■ Technical Manual Façade Sealing
Notes on Application / Limitations	<p>SikaHyflex®-250 Facade can be over-painted with most conventional paint systems. The paint must be tested for compatibility by carrying out preliminary trials and the best results are obtained if the sealant is allowed to cure fully first. Please note that non-flexible paint systems may impair the elasticity of the sealant and lead to cracking of the paint film.</p> <p>Colour deviations may occur due to exposure to chemicals, high temperatures, UV-radiation (especially with colour shade white). However a change in colour will not adversely influence the technical performance or the durability of the product.</p> <p>Before using on natural stone contact our Technical Service.</p> <p>Do not use SikaHyflex®-250 Facade on bituminous substrates, natural rubber, EPDM rubber or on building materials which might bleed oils, plasticisers or solvents which could attack the sealant. Do not use SikaHyflex®-250 Facade to seal swimming pools. SikaHyflex®-250 Facade is not suitable for joints with water pressure or permanent water immersion.</p> <p>Do not expose uncured SikaHyflex®-250 Facade to alcohol containing products as they may interfere with the curing reaction.</p>

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika® products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request. For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.



Sika Singapore Pte Ltd
200 Pandan Loop, 06-02 Pantech 21
Singapore 128388
SINGAPORE

Phone: +65 6777 2811
Fax: +65 6779 6200
e-mail: info@sg.sika.com
www.sika.com.sg



Sika Kimia Sdn Bhd
Lot 689 Nilai Industrial Estate
71800 Nilai, Negeri Sembilan DK
MALAYSIA

Phone: +606-7991762
Fax: +606-7991980
e-mail: info@my.sika.com
www.sika.com.my

